

Technical Data Sheet



Eclectic Products LLC
Manufacturing Facility
101 Dixie Mae Drive
Pineville, Louisiana
eclecticproducts.com
800.349.4667

ISO 9001:2015
Compliant
Quality Management
Systems

Administration Office
Eugene, Oregon
eclecticproducts.com
800.693.4667

UNITED STATES



2.0 fl oz carded tube
1.0 fl oz carded tube

Not all styles/sizes/colors available in all areas

QUICKHOLD

CONTACT ADHESIVE & SEALANT

PRODUCT DESCRIPTION

QuickHold has a super strong bond like traditional E6000, but with a thin consistency and fast set time.

WHERE TO USE / APPLICATIONS

- Adhere stones and gems to fashion jewelry
- Assemble plastic and wood craft kits
- Affix delicate embellishments to projects
- Fix cracks in ceramic bowls and pottery and much more!

FEATURES AND BENEFITS

FAST DRY TIME – creates a strong, secure bond quickly

WATER RESISTANT – immediately upon application; safe to use in and around water

ABRASION RESISTANT – maintains bond strength even on objects subject to wear

PAINTABLE – can paint over in 8 hours

TECHNICAL INFORMATION

PROPERTIES	
UNCURED MATERIAL	
Color:	Clear
VOC:	410 grams/liter
Solvent:	Methyl Ethyl Ketone (MEK) and Acetone
Flammable:	Yes
Density:	7.86 lbs/gal
Solids:	35% by weight, 24.3% by volume
Viscosity:	3,000 cps
Tack time:	2 – 3 minutes
Full cure time:	Thin film: 2 - 3 hours / Thick film: 3 - 6 hours
Storage:	Ideal temperature range: 50 to 80 °F (10 and 27 °C). Product may thicken when stored in colder temperatures but will not freeze. If product thickens from colder temperatures, warm to room temperature before use.
Freeze/thaw stability:	Stable, allow product to warm to room temperature before using
Shelf life:	2 years (unopened)
CURED MATERIAL	
Chemical resistance:	Excellent to water, dilute bases
UV resistance:	None; paint-over for UV resistance
Hardness:	90 Shore A
Tensile strength:	7250 lb/in ² (ASTM D-412)
Elongation:	25% (ASTM D-412)
Service temperature:	-40 to 150 °F (-40 to 66 °C)
Paint-over time:	8 hours

Technical Data Sheet

QUICKHOLD

CONTACT ADHESIVE & SEALANT

AUSTRALIA/NZ



59.1 mL carded tube

Not all styles/sizes/colors available in all areas.

CHEMICALS THAT HAVE LITTLE OR NO EFFECT ON QUICK HOLD

Acetic acid (5% and 10%)	QuickHOLD exhibits excellent resistance to water, dilute acids and dilute bases. Thin films of QuickHOLD were immersed in various chemicals for two weeks and exhibited weight gains of less than 2% and tensile strength loss of less than 10%. These chemicals are listed on the left. All percentages are given by weight unless otherwise noted.
Ammonium hydroxide (3.4%)	
Ammonium nitrate (50%)	
Antifreeze	
Beer (3.2% alcohol by volume)	
Boric acid (3.1%)	
Distilled water	
Hydraulic oil	
Lactic acid (3.8%)	
Milk (fresh, tested at 40 °F)	
Motor oil (30w)	
Nitric acid (10% and 20%)	
Oxalic acid (3.1%)	
Phosphoric acid (30% and 60% as P ₂ O ₅)	
Potassium hydroxide (3.4%)	
Sodium carbonates (2.7%)	
Sodium chloride (10%)	
Sulfuric acid (3% and 10%)	
Wine (20% alcohol by volume)	

SOLVENTS THAT DISSOLVE QUICK HOLD

Chevron solvent 1100	These are common solvents that dissolve QuickHOLD when hardened samples were immersed. The dissolution with these solvents was not instantaneous and therefore does not preclude usage in all cases. Applications were an occasional splash or brief exposure is expected may be acceptable. Test a small area before full use.
Chlorothane NU	
Cyclohexane	
Gasoline	
Methylene chloride	
Perchloroethylene	
Propyl acetate	
Toluene	
1, 1, 1-Trichloroethane	

DIRECTIONS and APPLICATION NOTES

Read directions and test small area before use. Hold tube upright when not in use.

- Step 1 Spread coating on each surface to be joined together
- Step 2 Allow to cure 1 to 2 minutes.
- Step 3 Press both surfaces together.
QuickHOLD hardens by solvent evaporation and forms an immediate bond which is
- Step 4 difficult to reposition after both adhesive coated surfaces are placed in contact and sufficient pressure is exerted to create full contact between both surfaces.

For technical assistance, call 800.767.4667.

- Please read all directions before using. Use in well-ventilated area.
- May damage finished surfaces. Avoid such contact until completely cured. Not recommended for use on Styrofoam™, polystyrene, polyethylene, polypropylene or polypropylene plastics, or paper products; and any items that come into contact with food, drinking water or animals.
- Cures by solvent evaporation.



QUICKHOLD

CONTACT ADHESIVE & SEALANT

HEALTH and SAFETY

This product contains MEK (Methyl Ethyl Ketone) and Acetone.

Before working with this product, read and become familiar with information concerning hazards, proper use and handling.

To request a hard copy of the SDS, please send an e-mail to sds@eclecticproducts.com.

⚠WARNING: This product can expose you to chemicals including acetaldehyde which is known to the State of California to cause cancer. For more information go to www.p65warnings.ca.gov.

LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. The manufacturer will not accept liability for more than product replacement. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products LLC, P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure. This warranty gives you specific legal rights, and you also have other rights, which vary from province to province.