Technical

Data Sheet

E6000 INDUSTRIAL ADHESIVE



Self-Leveling Formula (Black)

ECLECTIC IN THE HOME & ON THE JOB PRADUCTS

Eclectic Products, Inc.
Manufacturing Facility
101 Dixie Mae Drive
Pineville, Louisiana
eclecticproducts.com
800.349.4667

ISO 9001:2015 Compliant

Quality Management Systems

Administration Office Eugene, Oregon eclecticproducts.com 800.693.4667 Technical Service

UNITED STATES/MEXICO

800.767.4667



3.7 fl oz (Black) 10.2 fl oz (Black) Not all styles/sizes/colors available in all areas.

PRODUCT DESCRIPTION

E6000 is a unique SELF-LEVELING, non-flammable industrial adhesive formulated to meet high-performance requirements. It permanently adheres to more surfaces than virtually any other adhesive, providing exceptional adhesion to wood, metal, glass, fiberglass, ceramics, masonry, concrete, asphalt, leather, rubber, PVC, neoprene, vinyl and many plastics. E6000 maintains its flexible bond in extreme cold temperatures, will not crack or become brittle and is excellent for bonding items subject to vibration. For applications that are exposed to direct sunlight, paint over E6000 after curing or use E6800 UV formula.

WHERE TO USE / APPLICATIONS

- general facility/building repair
- flooring repairs
- locking down fasteners against vibration
- trailer repair
- auto upholstery/paneling/molding
- and much more!

FEATURES AND BENEFITS

EASY TO USE – easy squeeze tube (1.0 or 3.7 fl oz tube) or cartridge gun (10.2 fl oz cartridge)

FLEXIBLE – does not become brittle in cold weather and bonds items subject to vibration

CHEMICAL RESISTANT – safe for applications exposed to dilute acids and dilute caustics

ABRASION RESISTANT – great for bonding objects subject to normal wear

PAINTABLE – paint to match surrounding area or to make UV resistant

TECHNICAL INFORMATION

PROPERTIES – Low / Medium / High Viscosity					
UNCURED MATERIAL					
Color:	Black				
Solvent:	Perchloroethylene				
Non-flammable:	Yes (uncured liquid state)				
Density:	11.0 +/-0.1 lbs/gal				
Solids:	30% by weight, 40% by volume				
Viscosity:	50,000 cps low / 100,000 cps medium				
Tack time:	~ 4 minutes				
Set time:	20 minutes*				
Full cure time:	Thin film: 24 hours / Thick film: 48-72 hours				
Storage:	Product may thicken when stored in colder temperatures. If product				
	thickens from colder temperatures, warm to room temperature before				
	use.				
Application Temp:	Ideal application temperature range is 50 to 90 °F (10 to 32 °C).				
Freeze/thaw stability:	Stable, allow product to warm to room temperature before using				
Shelf life:	2 years (unopened)				

^{*}Depending on material, humidity and temperature.

Technical

E6000 INDUSTRIAL ADHESIVE

MEXICO USA

Data Sheet

Self-Leveling Formula (Black)

CURED MATERIAL				
Chemical resistance:	Excellent to dilute acids and dilute bases			
Hardness:	80 Shore A			
Dielectric strength:	400V/mil (ASTM D-149); this is the maximum voltage that can be applie			
	to a given material without causing it to break down			
Tensile strength:	3500 lb/in ² (ASTM D-412)			
Elongation:	900% (ASTM D-412)			
Service temperature:	Fully cured adhesive can withstand temperatures from -40 to 180 °F (-40			
	to 82 °C) intermittently.			

ADHESION TEST – 180° Peel Strength Test - ASTM D 903						
Aluminum	Birch (wood)	Glass	PVC	Steel		
35 pli	40 pli	34 pli	38 pli	45 pli		

Avg. Max Load Measured in pli (pounds per linear inch)

CHEMICALS THAT HAVE LITTLE OR NO EFFECT ON E6000

Acetic acid (5% and 10%) Ammonium hydroxide (3.4%) Ammonium nitrate (50%)

Antifreeze

Beer (3.2% alcohol by volume)

Boric acid (3.1%)
Distilled water
Hydraulic oil
Lactic acid (3.8%)

Milk (fresh, tested at 40 °F)

Motor oil (30w)

Nitric acid (10% and 20%)

Oxalic acid (3.1%)

Phosphoric acid (30% and 60% as P₂O₅)

Potassium hydroxide (3.4%) Sodium carbonates (2.7%) Sodium chloride (10%) Sulfuric acid (3% and 10%)

Wine (20% alcohol by volume)

E6000 exhibits excellent resistance to dilute acids and dilute bases. Thin films of E6000 were immersed in various chemicals for two weeks and exhibited weight gains of less than 2% and tensile strength loss of less than 10%. These chemicals are listed on the left. All percentages are given by weight unless otherwise noted.

SOLVENTS THAT DISSOLVE E6000

Chevron solvent 1100 Chlorothane NU Cyclohexane Gasoline Perchloroethylene Propyl acetate Toluene These are common solvents that dissolve E6000 when hardened samples were immersed. The dissolution with these solvents was not instantaneous and therefore does not preclude usage in all cases. Applications where an occasional splash or brief exposure is expected may be acceptable. Test a small area before full use.

DIRECTIONS and APPLICATION NOTES

Read directions and test small area before use.

- Step 1 Surface should be clean, dry and free of dirt. For best results, lightly roughen surface before use.
- Step 2 TUBE: Puncture inner seal using pointer cap (if tube has a foil seal). CARTRIDGE: Trim end of nozzle. Puncture inner seal.
 - Ideal application temperature range is 50 to 90 °F (10 to 32 °C). However, fully cured adhesive can withstand temperatures from 40 to 180 °F (-40 to 82 °C) intermittently.
- Step 3 Apply directly to surfaces to be bonded or repaired.
- Step 4 Allow 24 hours for curing. Depending on materials and temperature, maximum bond strength may not be reached for 48 to 72 hours.

Technical

E6000 INDUSTRIAL ADHESIVE



Data Sheet

Self-Leveling Formula (Black)

- Step 5 TUBE: For future easy cap removal, apply a thin coat of petroleum jelly to the threads of the tube before replacing the cap. CARTRIDGE: For prolonged storage after opening, cover or plug the opening of the nozzle.
- Step 6 Clean uncured adhesive with acetone or citrus-based solvents. Cured material may be removed by cutting or scraping.

HEALTH and SAFETY

This product contains perchloroethylene. Before working with this product, read and become familiar with information concerning hazards, proper use and handling.

To request a hard copy of the SDS, please send an e-mail to sds@eclecticproducts.com.

LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.