

Technical Data Sheet



Eclectic Products LLC
Manufacturing Facility
101 Dixie Mae Drive
Pineville, Louisiana
eclecticproducts.com
800.349.4667

ISO 9001:2015
Compliant
Quality Management
Systems

Administration Office
Eugene, Oregon
eclecticproducts.com
800.693.4667
Technical Service
800.767.4667



UNITED STATES/MEXICO

1.0 fl oz
3.7 fl oz

Not all styles/sizes/colors available in all areas.



AMAZING GOOP

ALL PURPOSE ADHESIVE

PRODUCT DESCRIPTION

AMAZING GOOP ALL PURPOSE Contact Adhesive & Sealant bonds with superior strength to most any material imaginable. It's perfect for just about any repair!

WHERE TO USE / APPLICATIONS

It's ideal for repairing everything around the house from broken teacups to loose towel racks. It's even sturdy enough to seal cracks in cement or adhere new handles on garden tools. AMAZING GOOP ALL PURPOSE adheres glass, plastic, metal, leather, vinyl, rubber, brick, marble, copper, brass, wood, porcelain, ceramic making it the most versatile and effective adhesive available. *

FEATURES AND BENEFITS

FLEXIBLE – does not become brittle in cold weather

CHEMICAL RESISTANT – safe for applications exposed to dilute acids and dilute caustics

ABRASION RESISTANT – great for bonding objects subject to normal wear

WATERPROOF – can be submerged in fresh and salt water after complete cure

WASHER/DRYER SAFE – safe for use on clothing, fabric and shoes; do not dry clean

**Not recommended for use on polystyrene, polyethylene, polypropylene, styrofoam™ or paper products.*

TECHNICAL INFORMATION

PROPERTIES – MEDIUM VISCOSITY

UNCURED MATERIAL	
Color:	Clear
Solvent:	Toluene, Petroleum Distillates (flammable)
Density:	7.4 lbs/gal
Solids:	45% by weight, 42% by volume
Viscosity:	100,000 cps
Tack time:	2 minutes
Set time:	45 minutes*
Full cure time:	Thin film: 24 hours / Thick film: 48-72 hours
Storage:	Product may thicken when stored in colder temperatures. If product thickens from colder temperatures, warm to room temperature before use.
Application Temp:	Ideal application temperature range is 50 to 90 °F (10 to 32 °C).
Freeze/thaw stability:	Stable, allow product to warm to room temperature before using
Shelf life:	2 years (unopened)
VOC:	489 g/L

**Depending on material, humidity and temperature.*

CURED MATERIAL

Chemical resistance:	Excellent to water, dilute acids & bases
UV resistance:	None; paint-over for UV resistance. Paint over time is 24 hours.
Hardness:	80 Shore A
Tensile Strength:	2,000 lbs/in ² (ASTM D-412)
Elongation %:	1,100% (ASTM D-412)
Dielectric strength:	400V/mil (ASTM D-149); this is the maximum voltage that can be applied to a given material without causing it to break down
Service temperature:	Fully cured adhesive can withstand temperatures from -40 to 180 °F (-40 to 82 °C) Intermittently.

Technical Data Sheet

AMAZING GOOP

ALL PURPOSE ADHESIVE

CANADA



AUSTRALIA/NZ



26.2 G

Not all styles/sizes/colors available in all areas.

ADHESION TESTING

SUBSTRATE	ADHESIVE DATA PLI & PSI	ASTM TEST #	ASTM TEST DESCRIPTION
FABRIC	30	1876	T-PEELS PLI
LEATHER	30		
VINYL	30		
CANVAS	45		
NEOPRENE	20		
RUBBER	10	D1002/3163	LAP SHEAR - PSI
METAL	210		
WOOD	200		
COPPER	150		
POLYMER CLAY	30		
LAMINATE	70		
PLASTICS	80		
FIBERGLASS	100		
PVC	100		
CERAMIC	380		
CONCRETE	280		
MASONRY	110		
ASPHALT	200		
GLASS	200		

CHEMICALS THAT HAVE LITTLE OR NO EFFECT ON AMAZING GOOP

Acetic acid (5% and 10%)
 Ammonium hydroxide (3.4%)
 Ammonium nitrate (50%)
 Antifreeze
 Beer (3.2% alcohol by volume)
 Boric acid (3.1%)
 Distilled water
 Hydraulic oil
 Lactic acid (3.8%)
 Milk (fresh, tested at 40 °F)
 Motor oil (30w)
 Nitric acid (10% and 20%)
 Oxalic acid (3.1%)
 Phosphoric acid (30% and 60% as P₂O₅)
 Potassium hydroxide (3.4%)
 Sodium carbonates (2.7%)
 Sodium chloride (10%)
 Sulfuric acid (3% and 10%)
 Wine (20% alcohol by volume)

SOLVENTS THAT DISSOLVE AMAZING GOOP

Chevron solvent 1100
Chloroethane NU
Cyclohexane
Gasoline
Perchloroethylene
Propyl acetate
Toluene

DIRECTIONS and APPLICATION NOTES

Read directions and test small area before use.

1. Surface should be clean, dry and free of dirt. For best results, lightly roughen surface before use.
2. Puncture seal in neck of tube using pointer cap. Ideal application temperature range is 50 to 90 °F (10 to 32 °C). However, fully cured adhesive can withstand temperatures from -40 to 180 °F (-40 to 82 °C) intermittently.
3. Apply directly to each surface to be bonded or repaired. Allow to partially cure, approximately 2 minutes before mating surfaces. Hardens by solvent evaporation and forms an immediate bond that is difficult to reposition after both adhesive-coated surfaces are placed in contact with each other and sufficient pressure is exerted to establish full contact.
4. Allow 24 hours for curing. Depending on materials and temperature, maximum strength may not be reached for 48 to 72 hours.
5. For future easy cap removal, apply a thin coat of petroleum jelly to the threads of the tube before replacing the cap.
6. Clean uncured adhesive with acetone or citrus-based solvents. Cured material may be removed by cutting or scraping.

Note: May damage finished surfaces. Avoid such contact until completely dry. Not recommended for use on polystyrene, polyethylene, polypropylene, Styrofoam™ on paper products. Not recommended for any items that come into contact with food, drinking water or animals.

Do not dry clean.

HEALTH and SAFETY

This product contains toluene. Before working with this product, read and become familiar with information concerning hazards, proper use and handling.

To request a hard copy of the SDS, please send an e-mail to sds@eclecticproducts.com.

⚠WARNING: This product can expose you to chemicals including toluene which is known to the State of California to cause birth defects or other reproductive harm. For more information go to www.p65warnings.ca.gov.

LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.