

# Technical Data Sheet



Eclectic Products, Inc.  
Manufacturing Facility  
101 Dixie Mae Drive  
Pineville, Louisiana  
eclecticproducts.com  
800.349.4667

ISO 9001:2015  
Compliant  
Quality Management Systems

Administration Office  
Eugene, Oregon  
eclecticproducts.com  
800.693.4667  
Technical Service  
800.767.4667



UNITED STATES/ MEXICO



3.7 fl oz

Not all styles/sizes/colors available in all areas.

# AMAZING GOOP

## AUTOMOTIVE ADHESIVE

### PRODUCT DESCRIPTION

AMAZING GOOP AUTOMOTIVE is scientifically formulated to permanently seal a variety of materials used in and around automobiles.

### WHERE TO USE / APPLICATIONS

Use in and around automobiles to stop tears in vinyl seats, floor mats and convertible tops. AMAZING GOOP AUTOMOTIVE can also coat terminals on batteries.\*

### FEATURES AND BENEFITS

**FLEXIBLE** – does not become brittle in cold weather

**CHEMICAL RESISTANT** – safe for applications exposed to dilute acids and dilute caustics

**ABRASION RESISTANT** – great for bonding objects subject to normal wear

**WATERPROOF** – can be submerged in fresh and salt water after complete cure

*\*Not recommended for use on polystyrene, polyethylene, polypropylene, styrofoam™ or paper products.*

### TECHNICAL INFORMATION

PROPERTIES – MEDIUM VISCOSITY	
UNCURED MATERIAL	
Color:	Clear
Solvent:	Toluene, Petroleum Distillates (flammable)
Density:	7.4 lbs/gal
Solids:	45% by weight, 42% by volume
Viscosity:	100,000 cps
Tack time:	2 minutes
Set time:	45 minutes*
Full cure time:	Thin film: 24 hours / Thick film: 48-72 hours
Storage:	Product may thicken when stored in colder temperatures. If product thickens from colder temperatures, warm to room temperature before use.
Application Temp:	Ideal application temperature range is 50 to 90 °F (10 to 32 °C).
Freeze/thaw stability:	Stable, allow product to warm to room temperature before using
Shelf life:	2 years (unopened)
VOC:	489 g/L

*\*Depending on material, humidity and temperature.*

CURED MATERIAL	
Chemical resistance:	Excellent to water, dilute acids & bases
UV resistance:	None; paint-over for UV resistance. Paint over time is 24 hours.
Hardness:	80 Shore A
Tensile Strength:	2,000 lbs/in <sup>2</sup> (ASTM D-412)
Elongation %:	1,100% (ASTM D-412)
Dielectric strength:	400V/mil (ASTM D-149); this is the maximum voltage that can be applied to a given material without causing it to break down
Service temperature:	Fully cured adhesive can withstand temperatures from -40 to 180 °F (-40 to 82 °C) Intermittently.

# Technical Data Sheet

# AMAZING GOOP

## AUTOMOTIVE ADHESIVE

CANADA



109.4 mL Clear & Black

Not all styles/sizes/colors available in all areas.

### ADHESION TESTING

SUBSTRATE	ADHESIVE DATA PLI & PSI	ASTM TEST #	ASTM TEST DESCRIPTION
FABRIC	30	1876	T-PEELS PLI
LEATHER	30		
VINYL	30		
CANVAS	45		
NEOPRENE	20		
RUBBER	10	D1002/3163	LAP SHEAR - PSI
METAL	210		
WOOD	200		
COPPER	150		
POLYMER CLAY	30		
LAMINATE	70		
PLASTICS	80		
FIBERGLASS	100		
PVC	100		
CERAMIC	380		
CONCRETE	280		
MASONRY	110		
ASPHALT	200		
GLASS	200		

### CHEMICALS THAT HAVE LITTLE OR NO EFFECT ON AMAZING GOOP

- Acetic acid (5% and 10%)
- Ammonium hydroxide (3.4%)
- Ammonium nitrate (50%)
- Antifreeze
- Beer (3.2% alcohol by volume)
- Boric acid (3.1%)
- Distilled water
- Hydraulic oil
- Lactic acid (3.8%)
- Milk (fresh, tested at 40 °F)
- Motor oil (30w)
- Nitric acid (10% and 20%)
- Oxalic acid (3.1%)
- Phosphoric acid (30% and 60% as P<sub>2</sub>O<sub>5</sub>)
- Potassium hydroxide (3.4%)
- Sodium carbonates (2.7%)
- Sodium chloride (10%)
- Sulfuric acid (3% and 10%)
- Wine (20% alcohol by volume)

# AMAZING GOOP

---

## AUTOMOTIVE ADHESIVE

---

---

### SOLVENTS THAT DISSOLVE AMAZING GOOP

---

Chevron solvent 1100  
Chlorothane NU  
Cyclohexane  
Gasoline  
Perchloroethylene  
Propyl acetate  
Toluene

---

---

### DIRECTIONS and APPLICATION NOTES

---

Read directions and test small area before use.

1. Surface should be clean, dry and free of dirt. For best results, lightly roughen surface before use.
2. Puncture seal in neck of tube using pointer cap. Ideal application temperature range is 50 to 90 °F (10 to 32 °C). However, fully cured adhesive can withstand temperatures from -40 to 180 °F (-40 to 82 °C) intermittently.
3. Apply directly to each surface to be bonded or repaired. Allow to partially cure, approximately 2 minutes before mating surfaces. Hardens by solvent evaporation and forms an immediate bond that is difficult to reposition after both adhesive-coated surfaces are placed in contact with each other and sufficient pressure is exerted to establish full contact.
4. Allow 24 hours for curing. Depending on materials and temperature, maximum strength may not be reached for 48 to 72 hours.
5. For future easy cap removal, apply a thin coat of petroleum jelly to the threads of the tube before replacing the cap.
6. Clean uncured adhesive with acetone or citrus-based solvents. Cured material may be removed by cutting or scraping.

Note: May damage finished surfaces. Avoid such contact until completely dry. Not recommended for use on polystyrene, polyethylene, polypropylene, Styrofoam™ on paper products. Not recommended for any items that come into contact with food, drinking water or animals.

---

### HEALTH and SAFETY

---

This product contains toluene. Before working with this product, read and become familiar with information concerning hazards, proper use and handling.

To request a hard copy of the SDS, please send an e-mail to [sds@eclecticproducts.com](mailto:sds@eclecticproducts.com).

**⚠WARNING:** This product can expose you to chemicals including toluene which is known to the State of California to cause birth defects or other reproductive harm. For more information go to [www.p65warnings.ca.gov](http://www.p65warnings.ca.gov).

---

### LIMITED WARRANTY

---

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.

---