

# Technical

# Data Sheet



Eclectic Products LLC  
Manufacturing Facility  
101 Dixie Mae Drive  
Pineville, Louisiana  
eclecticproducts.com

Customer Service  
1-800-349-4667

Technical Support  
1-800-767-4667

Administration Office  
Eugene, Oregon  
1-800-693-4667

ISO 9001:2015  
Compliant  
Quality Management Systems



UNITED STATES/MEXICO



1.0 fl oz

Not all styles/sizes/colors available in all areas

# AMAZING GOOP

## TRIM REPAIR ADHESIVE

### PRODUCT DESCRIPTION

Amazing GOOP TRIM Repair is a super strong, flexible and durable formula that will not crack or break under stress, road vibrations or temperature extremes. The nozzle tip makes it a great adhesive for precision and hard-to-reach applications.

### WHERE TO USE / APPLICATIONS

TRIM Repair permanently repairs loose and detached trim, weather-stripping, and most anything that should be attached to an automobile. Works great on chrome, wood, plastic, metal, rubber and more!\*

### FEATURES AND BENEFITS

**PERMANENT** – Super strong to multiple materials.

**EXTREME FLEX** – Does not become brittle even in cold weather; keeps its bond even under stress.

**WATERPROOF** – Formula is waterproof – even in outdoor conditions.

**PRECISION APPLICATION** – Nozzle tip allows for precision applications.

**WASHER/DRYER SAFE** – safe for use on clothing and fabrics; do not dry clean

*\*Not recommended for use on polystyrene, polyethylene, polypropylene, Styrofoam™ or paper products.*

## TECHNICAL INFORMATION

PROPERTIES – Low Viscosity	
UNCURED MATERIAL	
Color:	Clear
Solvent:	Toluene, Petroleum Distillates (flammable)
Density:	7.4 lbs/gal
Solids:	45% by weight, 42% by volume
Viscosity:	Low Viscosity: 50,000 cps
Tack time:	~ 2 minutes
Set time:	45 minutes*
Full cure time:	Thin film: 24 hours / Thick film: 48-72 hours
Storage:	Product may thicken when stored in colder temperatures. If product thickens from colder temperatures, warm to room temperature before use.
Application Temp:	Ideal application temperature range is 50 to 90 °F (10 to 32 °C).
Freeze/thaw stability:	Stable, allow product to warm to room temperature before using
Shelf life:	2 years (unopened)
VOC:	484 g/L

*\*Depending on material, humidity and temperature.*

CURED MATERIAL	
Chemical resistance:	Excellent to water, dilute acids and dilute bases
Hardness:	80 Shore A
Tensile Strength:	2,300 lb/sq <sup>2</sup> (ASTM D-412)
Elongation %:	800% (ASTM D-412)
Dielectric strength:	400V/mil (ASTM D-149); this is the maximum voltage that can be applied to a given material without causing it to break down
Service temperature:	Fully cured adhesive can withstand temperatures from -40 to 180 °F (-40 to 82 °C) intermittently.

**AMAZING GOOP**  
TRIM REPAIR ADHESIVE

**ADHESION TESTING**

UBSTRATE	ADHESIVE DATA PLI & PSI	ASTM TEST #	ASTM TEST DESCRIPTION
FABRIC	30	1876	T-PEELS PLI
LEATHER	30		
VINYL	25		
CANVAS	45		
NEOPRENE	20		
RUBBER	15		
METAL	200	D1002/3163	LAP SHEAR - PSI
WOOD	230		
POLYMER CLAY	30		
LAMINATE	70		
RESIN	140		
CHROME	150		
PLASTICS	100		
FIBERGLASS	100		
PVC	90	D1583	DOLLY PULL - PSI
CERAMIC	300		
CONCRETE	390		
MASONRY	350		
ASPHALT	250		
GLASS	215		

**CHEMICALS THAT HAVE LITTLE OR NO EFFECT ON  
AMAZING GOOP TRIM REPAIR**

Acetic acid (5% and 10%)  
 Ammonium hydroxide (3.4%)  
 Ammonium nitrate (50%)  
 Antifreeze  
 Beer (3.2% alcohol by volume)  
 Boric acid (3.1%)  
 Distilled water  
 Hydraulic oil  
 Lactic acid (3.8%)  
 Milk (fresh, tested at 40 °F)  
 Motor oil (30w)  
 Nitric acid (10% and 20%)  
 Oxalic acid (3.1%)  
 Phosphoric acid (30% and 60% as P<sub>2</sub>O<sub>5</sub>)  
 Potassium hydroxide (3.4%)  
 Sodium carbonates (2.7%)  
 Sodium chloride (10%)  
 Sulfuric acid (3% and 10%)  
 Wine (20% alcohol by volume)

# AMAZING GOOP

## TRIM REPAIR ADHESIVE

---

---

### SOLVENTS THAT DISSOLVE AMAZING GOOP TRIM REPAIR

---

Chevron solvent 1100  
Chlorothane NU  
Cyclohexane  
Gasoline  
Perchloroethylene  
Propyl acetate  
Toluene

---

---

### DIRECTIONS and APPLICATION NOTES

---

Read directions and test small area before use.

1. Surface should be clean, dry and free of dirt. For best results, lightly roughen surface before use.
2. Puncture seal in neck of tube using pointer cap. Ideal application temperature range is 50 to 90 °F (10 to 32 °C). However, fully cured adhesive can withstand temperatures from -40 to 180 °F (-40 to 82 °C) intermittently.
3. Apply directly to each surface to be bonded or repaired. Allow to partially cure, approximately 2 minutes before mating surfaces. Hardens by solvent evaporation and forms an immediate bond that is difficult to reposition after both adhesive-coated surfaces are placed in contact with each other and sufficient pressure is exerted to establish full contact.
4. Allow 24 hours for curing. Depending on materials and temperature, maximum strength may not be reached for 48 to 72 hours.
5. For future easy cap removal, apply a thin coat of petroleum jelly to the threads of the tube before replacing the cap.
6. Clean uncured adhesive with acetone or citrus-based solvents. Cured material may be removed by cutting or scraping.

Note: May damage finished surfaces. Avoid such contact until completely dry. Not recommended for use on polystyrene, polyethylene, polypropylene, Styrofoam™ on paper products. Not recommended for any items that come into contact with food, drinking water or animals.

Do not dry clean.

---

### HEALTH and SAFETY

---

This product contains toluene. Before working with this product, read and become familiar with information concerning hazards, proper use and handling.

To request a hard copy of the SDS, please send an e-mail to [sds@eclecticproducts.com](mailto:sds@eclecticproducts.com).

**⚠WARNING:** This product can expose you to chemicals including toluene which is known to the State of California to cause birth defects or other reproductive harm. For more information go to [www.p65warnings.ca.gov](http://www.p65warnings.ca.gov).

---

### LIMITED WARRANTY

---

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.